



Sales Specification

Product: *EPOLENE*® EE-2 Polymer

Specification: EE-2

Effective Date: 27-July-07

Version: 6

Pages: 1 of 1

A. GENERAL

A-1 This specification replaces Sales Specification EE-2 Version 5, dated February 15, 2006. This revision is being done to reflect an ownership change.

A-2 This specification describes a grade of polymer that meets all of the requirements listed in Section B when tested as directed by the referenced methods.

B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
B-1	Softening Point, °C	106.0 - 120.0	PTM-005
B-2	Color, Gardner	10.0 MAX	VCC-099
B-3	Viscosity @ 125C, CPS	1000 - 2500	V-005

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.