



Sales Specification

Product: *EPOLENE*® C-15P Polymer

Specification: C-15
Effective Date: 15-Feb-06
Version: 6
Pages: 1 of 1

A. GENERAL

- A-1** This specification replaces Sales Specification C-15 Version 5, dated September 2001. This revision is being done to reflect a standardized product name.
- A-2** This specification describes a grade of *EPOLENE* Polymer, which meets all of the requirements listed in Section B when tested as directed by the referenced methods.

B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
B-1	Softening Point, °C	92.0 - 105.0	PTM-005
B-2	Viscosity @ 150C, CPS	3000 - 4800	V-005
B-3	Color, Gardner	1.0 MAX	VCC-099
B-4	Retained on 18 mesh %	< 0.49	GA-032

used in accordance with safety precautions recommended by their manufacturers.