



Westlake Chemical Corporation
Longview Plant
P.O. Box 8388
Longview, TX 75607
TS&D 903 237 6425

Sales Specification

Product: *EPOLENE*® C-16 Polymer

Specification: C-16
Effective Date: 15-Feb-06
Version: 8
Pages: 1 of 1

A. GENERAL

- A-1 This specification replaces Sales Specification C-16 Version 7, dated January 2001. This revision is being done to reflect a standardized product name.
- A-2 This specification describes a grade of *EPOLENE* Polymer, which meets all of the requirements listed in Section B when tested as directed by the referenced methods.

B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
B-1	Acid Number, mg-KOH	1.5 - 2.5	VA-145
B-2	Softening Point, °C	98.0 - 106.0	PTM-005
B-3	Viscosity @ 150C, CPS	6300 - 10000	V-005
B-4	Color, Gardner	1.0 MAX	VCC-099

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.