



# Sales Specification

---

<b>Product:</b> <i>EPOLENE</i> ® E-10 Polymer	<b>Specification:</b> E-10
	<b>Effective Date:</b> 15-Aug-07
	<b>Version:</b> 10
	<b>Pages:</b> 1 of 1

---

## A. GENERAL

- A-1** This specification replaces Sales Specification E-10 Version 9, dated May 2006. This revision is being done to reflect a standardized product name.
- A-2** This specification describes a grade of EPOLENE Polymer, which meets all of the requirements listed in Section B when tested as directed by the referenced methods.

## B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
<b>B-1</b>	Acid Number, mg-KOH	14.0 - 18.5	VA-145
<b>B-2</b>	Viscosity @ 125C, CPS	650 - 1200	V-005
<b>B-3</b>	Color, Gardner	2.0 MAX	VCC-099
<b>B-4</b>	High Pressure Emulsion, %T	60 MIN	TBA-010

---

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.