



Sales Specification

Product: *EPOLENE*® E-14EP Polymer, Emulsion Grade

Specification: E-14EP
Effective Date: 5-Aug-2008
Version: 2
Pages: 1 of 1

A. GENERAL

A-1 This specification replaces Sales Specification E-14EP Version 2, dated February 2006. This revision is being done to reflect a standardized product name.

A-2 This specification describes a grade of *EPOLENE* Polymer, which meets all of the requirements listed in Section B when tested as directed by the referenced methods.

B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
B-1	Acid Number, mg-KOH	14.0 - 18.5	VA-145
B-2	Softening Point, °C	100.6 - 105.0	VCC-99
B-3	Viscosity @ 125C, CPS	150 - 300	V-005
B-4	Color, Gardner	3.0 MAX	VCC-99
B-5	Retained on 18 Mesh, W%	0.49 MAX	GA-32

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.