



Sales Specification

Product: *EPOLENE*® E-20 Polymer

Specification: E-20
Effective Date: 15-Feb-06
Version: 9
Pages: 1 of 1

A. GENERAL

A-1 This specification replaces Sales Specification E-20 Version 8, dated April 2002. This revision is being done to reflect a standardized product name.

A-2 This specification describes a grade of *EPOLENE* Polymer, which meets all of the requirements listed in Section B when tested as directed by the referenced methods.

B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
B-1	Softening Point, °C	106.0 - 114.0	PTM-005
B-2	Acid Number, mg-KOH	14.0 - 18.5	VA-145
B-3	Viscosity @ 125C, CPS	1000 - 2000	V-005
B-4	Color, Gardner	2.0 MAX	VCC-099
B-5	Cationic Emulsion E-20, %T	50.0 MIN	TBA-012

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.