



Sales Specification

Product: *EPOLENE*® E-43P Polymer

Specification: E-43P
Effective Date: 15-Feb-06
Version: 8
Pages: 1 of 1

A. GENERAL

- A-1 This specification replaces Sales Specification E-43 Version 7, dated January 2001. This revision is being done to reflect a standardized product name.
- A-2 This specification describes a grade of *EPOLENE* Polymer, which meets all of the requirements listed in Section B when tested as directed by the referenced methods.

B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
B-1	Acid Number, mg-KOH	40.0 - 55.0	VA-145
B-2	Softening Point, °C	153.0 - 162.0	PTM-005
B-3	Color, Gardner	11.0 MAX	VCC-099
B-4	Viscosity @ 190C, CPS	150 - 700	V-005
B-5	Retained on 18 mesh, %	<0.49 %	GA-032

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.