



Sales Specification

Product: *EPOLENE*® N-11 Polymer

Specification: N-11
Effective Date: 15-Feb-06
Version: 6
Pages: 1 of 1

A. GENERAL

- A-1 This specification replaces Sales Specification N-11 Version 5, dated April 2002. This revision is being done to reflect a standardized product name.
- A-2 This specification describes a grade of *EPOLENE* Polymer, which meets all of the requirements listed in Section B when tested as directed by the referenced methods.

B. PROPERTIES AND TEST METHODS

	<u>Property</u>	<u>Specification Limits</u>	<u>Test Method</u>
B-1	Softening Point, °C	104.0- 112.0	PTM-005
B-2	Viscosity @ 125C, CPS	250 - 450	V-005
B-3	Color, Gardner	2.0 MAX	VCC-099

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.