



## Sales Specification

---

**Product:** *EPOLENE*® N-15P Polymer

**Specification:** N-15P  
**Effective Date:** 15-Feb-06  
**Version:** 6  
**Pages:** 1 of 1

---

### **A. GENERAL**

- A-1 This specification replaces Sales Specification N-15 Version 5, dated April 2002. This revision is being done to reflect a standardized product name.
- A-2 This specification describes a grade of *EPOLENE* Polymer, which meets all of the requirements listed in Section B when tested as directed by the referenced methods.

### **B. PROPERTIES AND TEST METHODS**

	<b><u>Property</u></b>	<b><u>Specification Limits</u></b>	<b><u>Test Method</u></b>
B-1	Softening Point, °C	160.0 - 170.0	PTM-005
B-2	Viscosity @ 190C, CPS	250 - 950	V-005
B-3	Color, Gardner	2.0 MAX	VCC-099
B-4	Retained on 18 Mesh, W%	0.49 MAX	GA-032

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.