



Product Data Sheet Epolene® C-26 Polymer

Application/Uses

- Automotive
- Building and Construction
- Rubber and Plastic Modification

Key Attributes

- Balances attraction between polar fillers / reinforcements and non polar polymers
- Coupling agent for PE composites
- Maleic anhydride grafted polyethylene (PE)

Product Description

Epolene C-26 is a maleic anhydride grafted polyethylene coupling agent for polyethylene (PE) composites. The polar functionality and molecular weight are optimized to provide balanced attraction between PE and reinforcements / fillers like glass, wood, minerals, and metals. *Epolene C-26* Polymers are products of Westlake Chemical Corporation and are protected under one or more of the following U.S. patents: 5,955,547 and 6,046,279; and their foreign equivalents.

Typical Properties

Property	Test Method	Typical Value, Units
Polymer Type		Ma-PE
Acid Number (mg KOH/g)		8
Ring and Ball Softening Point		122 DSC Tm, °C
Penetration Hardness ^a	ASTM D 5	<1 dmm
Viscosity, Brookfield ^b		
@ 125°C (257°F)		Solid @ this temp
@ 190°C (374°F)		MI = 8
Molecular Weight ^c M _w		65,000

^a Needle under 100-g load for 5s @ 25 deg C, tenths of mm

^b MI = Melt Index @ 190 deg C, 2.16 kg weight

^c Molecular weight measured via Gel Permeation Chromatography (GPC) using polystyrene standards

Compatibility and Solubility

Epolene polymers are compatible with many polymers, resins, and natural and synthetic waxes.

Packaging

Epolene C-26 is supplied as free-flowing pellets, packaged in multiwall paper bags with a polyethylene coated inner liner [22.67 kg (50 lb) net weight]. The bags are palletized and stretch wrapped to prevent contamination during storage and shipment.

Storage

The useful life of this product can be affected by storage and handling conditions. When stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures and contamination, this product is estimated to continue to meet applicable sales specifications for more than 3 years from the date of manufacture. First in first out (FIFO) inventory control is recommended.

It is your responsibility to determine that our product is safe, lawful and technically suitable for your intended uses. Please note that this letter is provided to you as one of the means to assist you in analyzing our product, and does not serve to modify or amend our sales contract or sales arrangement.

Westlake Polymers LLC does not endorse or claim suitability of its products for any particular application. **WESTLAKE MAKES NO WARRANTY OF MERCHANTABILITY AS TO ITS PRODUCTS. WESTLAKE POLYMERS LLC MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY or FITNESS OF ANY WESTLAKE PRODUCT FOR ANY PARTICULAR PURPOSE.** Westlake's liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.